



# AURA

Creating Possibilities, Delivering Excellence

**AURA GENERAL TRADING FZ- LLC**

**P.O.Box : 6542**

**Ras Al Khaimah - UAE**

**PH # +97155 416 0304**

**Email : Contact@aurauae.ae**

**TRN# 104641631700003**

**Web : aurauae.ae**

## Performance Benefits and Overview

AGT2080 – CaCO<sub>3</sub> Filler Masterbatch contains mainly CaCO<sub>3</sub> Calcium Carbonate powder, resin and some additives. CaCO<sub>3</sub> made natural mineral calcite with high pure over 99 %, high whiteness > 96 %, treatment surface by additive and use perfect technology. This product used to replace one of part virgin resin, from that help save cost for the end product and improved some properties such as: whiteness, hardness, strength.

CaCO <sub>3</sub> Powder Content	80±1%
Purity	96-98%
Mean particle size (D50)	2 µm
Carrier Resin	LLDPE
Melt Mass- Flow Rate (190°C/2.16kgs)	0.5-2 g/10 mins
Humidity	0.08 wt %
Processing Temperature	140-280°C

### Main Features

Good Dispersion	✓
Gloss Finish	✓
Food Contact	✓
Good Processability	✓
High Light Fastness	✓
Excellent Heat Resistance	✓
Increase Hardness	✓

Depending on processing parameters or local specifications. It is advisable to check with our sales to commercial production.

AGT2080	Polymer Compatibility			
	LLDPE	HDPE	LDPE	PP
	✓	✓	✓	✓

Standard Packaging	Certificate
25 kg bags (pallet 1350kg) Jumbo Bag ( 1200 kg)	FDA, REACH, EU NO 10/2011

Main Application	Properties	Dosage
Blow Film (Roll bags, T-shirt bags, Garbage bags)	PE Film thickness from 10 micron	Upto 12 %
	PE Film thickness from 40 micron	Upto 65 %
Injection Molding (HDPE Crates)		Upto 15 %
HDPE Blow Molding (Jerry cans/bottles)		Upto 25 %

The product should be stored in dry conditions at temperatures below 25°C protected from direct sunlight. If these protective measures are not taken into account impairment of the product is possible. This can result in degradation of the color, smell or loss of other properties. The data and information contained are presented in good faith, and are based on AURA General Trading FZ-LLC's current knowledge and experience. They are provided for guidance only. Because many factors may affect processing or application/use of the product. AURA General Trading FZ-LLC recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to us.

FOR & ON BEHALF OF

**AURA GENENERAL TRADING FZ-LLC**